

SCREEN FABRICS - TECHNICAL PARAMETRES

			Ts (%)		Rs (%)		As (%)		TV n-h	OF (%)
			A	B	A	B	A	B		
86 2043	bronze	Serge Ferrari	15	15	11	11	42	42	14	14
86 2044	white	Serge Ferrari	29	29	59	59	12	12	28	14
86 2047	anthracite	Serge Ferrari	17	17	7	7	76	76	16	14
86 2048	alu-alu	Serge Ferrari	19	19	39	39	42	42	20	14
86 2135	sandy beige	Serge Ferrari	24	24	39	39	37	37	28	14
92 2044	white	Serge Ferrari	19	19	68	68	13	13	18	4
92 2175	champagne	Serge Ferrari	19	19	65	65	16	16	18	4
92 2012	pepper	Serge Ferrari	7	7	30	30	63	63	5	4
92 2043	bronze	Serge Ferrari	4	4	13	13	83	83	5	4
92 2051	alu/white	Serge Ferrari	12	12	49	70	39	18	11	4
92 2046	alu/oat	Serge Ferrari	12	12	46	63	10	10	9	4
92 2048	alu/alu	Serge Ferrari	8	8	46	46	46	46	8	4
92 2074	alu/medium grey	Serge Ferrari	4	4	37	25	59	71	4	4
92 2068	alu/anthracite	Serge Ferrari	4	4	34	8	62	88	4	4
92 2045	beaten-metal	Serge Ferrari	4	4	35	35	61	61	4	4
92 2167	concrete	Serge Ferrari	6	6	19	19	75	75	5	4
92 2047	anthracite	Serge Ferrari	5	5	8	8	87	87	4	4
B92 1044	white	Serge Ferrari	-	-	70	70	30	30	-	0
B92 1046	alu	Serge Ferrari	-	-	49	49	51	51	-	0
B92 2171	boulder	Serge Ferrari	-	-	45	45	55	55	-	0
7635-52106	grey/charcoal	Serge Ferrari	6	6	12	9	82	85	5,9	5
7635-52101	white/white	Serge Ferrari	25		63		12		24,7	5
7635-52102	white/pearl	Serge Ferrari	19	19	53	48	28	33	16,7	5
7635-52142	grey/white	Serge Ferrari	11	11	26	35	63	54	9,9	5
7635-52143	deep black	Serge Ferrari	4		5		91		4,9	5
7635-52103	pearl/pearl	Serge Ferrari	16	16	38	38	46	46	13,3	5
7635-52104	pearl/grey	Serge Ferrari	11	11	29	24	60	65	9,6	5
7635-52105	grey/grey	Serge Ferrari	7	7	16	16	77	77	6,3	5
7635-52107	charcoal/charcoal	Serge Ferrari	6	6	6	6	88	88	6,3	5
7635-52108	charcoal/grey	Serge Ferrari	6	6	10	13	84	81	6,4	5
7635-52144	anthracite grey	Serge Ferrari	5	5	6	6	89	89	5,3	5
7635-52181	grey/sand	Serge Ferrari	6	6	22	27	72	67	5,2	5
7635-52171	white/sand	Serge Ferrari	17	17	52	45	31	38	15,6	5
7635-52177	sand/bronze	Serge Ferrari	6	6	26	18	68	76	5,6	5
7635-52174	linen/white	Serge Ferrari	21	21	62	63	17	16	20,8	5
7635-52172	pearl/linen	Serge Ferrari	16	16	44	48	40	36	13,2	5
7635-52173	linen/linen	Serge Ferrari	20	20	61	61	19	19	18,8	5
7635-52175	linen/grey	Serge Ferrari	11	11	43	32	46	57	10,6	5
7635-52176	sand/sand	Serge Ferrari	10	10	37	37	53	53	8	5
7635-52178	bronze/bronze	Serge Ferrari	4	4	7	7	89	89	3,7	5
7635-52179	bronze/pearl	Serge Ferrari	5	5	15	22	80	73	5	5
7635-52180	bronze/grey	Serge Ferrari	5	5	10	12	85	83	5	5
7635-52182	charcoal/bronze	Serge Ferrari	5	5	6	6	89	89	5,4	5
7605-51184	frost white	Serge Ferrari	9		59		32		8	5
7605-51187	natural	Serge Ferrari	7		37		56		7	5
7605-51188	macadamia	Serge Ferrari	5		29		66		4	5
7605-51194	shadow	Serge Ferrari	5		7		88		5	5
7605-51198	graphite black	Serge Ferrari	5		5		90		5	5

Ts Solar transmittance %

Rs Solar reflectance %

As Solar absorptance %

OF Openness Factor %

SCREEN FABRICS - FIRE CLASSIFICATION

Fire Classification	Standard	Result
---------------------	----------	--------

Soltis 86

Europe	EN 13501-1	B-s2,d0
France	UNE 23.727-90	M1
Germany	DIN 4102-1	B1
Weight	EN ISO 2286-2	380 ± 5 % g/m ²
Thickness	-	0,45 ± 5 % mm

Soltis 92

Europe	EN 13501-1	B-s2,d0
France	UNE 23.727-90	M1
Germany	DIN 4102-1	B1
Weight	EN ISO 2286-2	420 ± 5 % g/m ²
Thickness	-	0,45 ± 5 % mm

Soltis B92

Europe	EN 13501-1	B-s2,d0
Germany	DIN 4102-1	B1
Weight	EN ISO 2286-2	650± 5 % g/m ²
Thickness	-	0,60 ± 5 % mm

Soltis 7635

Europe	EN 13501-1	C-s3,d0
France	NF P 92-507	M1
Germany	DIN 4102-1	B1
Weight	EN ISO 2286-2	515 ± 5 % g/m ²
Thickness	-	0,73 ± 5 % mm

Soltis Veozip

Europe	EN 13501-1	B-s2,d0
France	NF P 92-507	M1
Germany	DIN 4102-1	B1
Weight	EN ISO 2286-2	580 ± 5 % g/m ²
Thickness	-	0,90 ± 5 % mm